



PHYSICAL PROPERTIES DATA SHEET

VAPORDRY™SA

Test	Test Standard	VAPORDRY™SA Performance
Tensile Strength	ASTM D 5034	Machine 120.6 lbf Crosswise 85.4 lbf
Water-ponding Test	AC48 section 4.4.1	Pass 61cm of water column for 48 hours
Water Vapor Transmission	ASTM E 96	14 perms
Air Permeance	ASTM E 2178	At 75 Pa calculated flow rate: 0.003 L/(s.m ²)
Nail Sealing	ASTM D 1970	Pass
<i>*Meets or exceeds the physical requirements of ASTM D 226 (type II), D 4869, and AC48</i>		

*Product to comply with $\pm$ 15% tolerance when evaluated with listed test standard.

UV rated: 120 days of exposure before installation of roofing

VAPORDRY™SA roll information:

- 4.75 ft width x 80 ft length x 25 mil thickness | 28 lbs/roll